POLYPLUS® 35

PREMIUM MODIFIED BITUMEN ADHESIVE

PRODUCT DESCRIPTION

PolyPlus 35 is a premium formulation designed for use as a cold-applied bonding adhesive for SBS modified bitumen base sheets and SBS modified bitumen smooth or granulated cap sheets. Its premium high gel formulation with SBS rubber is specifically formulated to be compatible with Polyglass roofing membranes.

USES

- Designed to apply SBS modified bitumen base sheets and SBS modified bitumen cap sheets
 to approved substrates such as structural concrete roof decks, existing smooth surface asphalt
 builtup roofs, certain roof insulations, glass fiber base sheets and other approved surfaces
- Suitable for use as an adhesive for APP sand back membranes
- Bonds gravel or mineral granules to BUR roof systems and modified cap sheets
- Not recommended for use with thermoplastic or thermoset membranes

FEATURES AND BENEFITS

- Adheres to substrate and superior lap shear adhesion
- Flexible with cohesive properties
- Eliminates the need for kettles and torches
- Excellent 24 hour strength; fully cured after 30 days
- Non-destructive to asphalt based roofing membranes
- Asbestos free 100% recycled cellulose fibers

TYPICAL PHYSICAL PROPERTIES

TEST PROPERTY	TEST VALUE	TEST PROCEDURE
Weight/gal (lb)	7.8 – 8.5	ASTM D2939
Solids Weight (%)	> 60	ASTM D1644
Flash Point (°F)	> 105	PMCC
VOC (gm/L)	< 300	Std Method
Viscosity (Stormer Seconds)	30 – 100	Stormer 550 gm/load /100 rev/77°F
Lap Shear Adhesion (lbf/in)	68	ASTM D3019, Type III

APPLICATION INSTRUCTIONS

Surface Preparation:

- Surfaces to receive coating must be clean, dry and free from any foreign matter such as dirt, oils, grease or other debris that could inhibit the adhesion capabilities of the newly installed products. Priming is recommended when adhering to questionable conditions.
- On existing roofs, inspect roof substrate condition. Blisters, buckles, and raised edges should be cut out and repaired for a smooth surface.
- Check all flashings, edges, drains, valleys and vents and repair as needed.
- Do not use on wet or damp surfaces, directly over wood or on surfaces previously covered with coal tar based products.







APPLICABLE STANDARDS

- Meets or exceeds the requirements of ASTM D3019 Type III
- Florida Building Code
- Miami-Dade County Product Control Approved







PACKAGING

• 4.75 Gallon (17.9 Liters) Pail





POLYPLUS® 35

PREMIUM MODIFIED BITUMEN ADHESIVE

Application:

- Stir well prior to application.
- Application Rate: Approximately 1.5 2 gallons per square when applied to smooth to semi-smooth surfaces. Coverage rate may vary depending on ambient temperature, surface porosity, as well as applicator and/or application technique.
- PolyPlus 35 may be applied by high pressure spray, notched squeegee, or brush application methods.
- After Adhesive Application: Apply membrane within 15 minutes
 of adhesive application. Unroll modified and base sheet rolls and
 allow them to relax prior to installation. Make sure that membrane is
 lying flat and making full contact with the adhesive. Roll all side and
 end laps making sure a sufficient amount of adhesive is applied so
 that a bead is visible at all lap edges.
- Two Layer Application: Install SBS base membrane in adhesive wait three to seven hours to allow adhesive to set before installing the SBS cap membrane.
- Slope Application: The adhesive may be used on various slopes up to 1½" per foot. Slopes greater than 1½" per foot will require back-nailing. Slopes less than or equal to 1½" per foot may require back-nailing. Please call Polyglass Technical Services should you have any questions on slope application.
- Apply only when ambient temperatures are 35°F and rising. Cold weather will cause product to stiffen, making application difficult.
- Do not apply if inclement weather is expected within 24 hours.
- Do not heat outside of container or attempt to thin this product. Not recommended for application on substrates that exceed 140°F.
- Close air intakes on roof until solvents dissipate. Solvent vapor can penetrate porous substrates. Make sure there is proper outside ventilation for the underside of this type of roof deck.

Limitations:

- Do not use with organic saturated felts.
- Do not use on TPO, EPDM, PVC, or other single ply membranes.
- Not to be installed over or under polystyrene insulation.

Storage and Cleaning:

- Product shelf life: 18 months from date of manufacture when properly stored.
- Do not store at temperatures greater than 120°F.
- Store 24 hours at room temperature prior to application.
- Observe normal safeguards for storing and handling of this product prior to and during application.
- Do not allow product to freeze. Discard if frozen.
- Keep containers covered when not in use.
- Clean equipment and contaminated surfaces with kerosene or mineral spirits.
- Clean hands with waterless hand cleaner.

For Professional Use Only - Keep out of the reach of children.

MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Phoenix, AZ
- Waco, TX
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc. 1111 West Newport Center Drive Deerfield Beach, FL 33442 www.polyglass.us

General Line: (888) 410-1375

(954) 233-1330

Customer Service: (800) 222-9782 Technical Service: (866) 794-9659

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects that result in the material not complying with product specifications for a period of 12 months.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances. The product user, and not Polyglass, is responsible for determining the suitability and compatibility of our products for the user's intended use.

For the most current product data and warranty information, visit www.polyglass.us

