

POLYSTICK® MTS

SELF-ADHERED HIGH TEMPERATURE ROOF UNDERLAYMENT

PRODUCT DESCRIPTION

Polystick MTS is a self-adhered waterproofing underlayment specifically designed for high temperatures roofs featuring metal, concrete and clay tiles. Polystick MTS is manufactured with patented ADESO® Technology, a dual-compound technology that incorporates a fiberglass mat that is embedded in a modified compound with an aggressive proprietary self-adhesive compound applied to the bottom surface of the membrane.

Polystick MTS features an slip resistant film surface and 180 day UV exposure rating. Featuring exceptional tensile strength and thermal stability, Polystick MTS is temperature resistant to 265°F. Polystick MTS has a film-free selvage edge on the top surface and a split release film on the bottom surface for easy installation.

TYPICAL APPLICATIONS

- Specifically designed as underlayment for high temperature environments
- Approved for application under metal, concrete and clay tile, and shingles
- Can be used as part of a multi-ply underlayment system
- Can be used for perimeter reinforcement and flashing details

FEATURES AND BENEFITS

- Patented ADESO Technology
- Approved up to 265°F
- 180 days exposure
- Exceptional tensile strength and thermal stability

TECHNICAL DESCRIPTION

TEST METHOD	PROPERTY	ASTM VALUE
ASTM D5147	Maximum Load, Longitudinal and Transverse, min, kN/m (lbf/in.)	4.4 (25)
ASTM D5147	Elongation at break, min of modified bitumen portion (%)	10
ASTM D5147	Tear Resistance, Longitudinal and Transverse, min, N (lbf)	89 (20)
ASTM E96	Moisture Vapor Permeability, max, perms	0.1
ASTM D1970	Adhesion to Plywood @ 40°F, min, lbf/ft width	2.0
ASTM D1970	Adhesion to Plywood @ 75°F, min, lbf/ft width	12.0
ASTM D1970	Sealability around nail	pass
ASTM D1970	Waterproof integrity after low temp flexibility	pass
ASTM D1970	Waterproof integrity of lap seam	pass
ASTM D1970	Slip Resistance	pass



PRODUCT DATA

Coverage (Approx) 200 sq ft
 Weight (Approx) 70 lbs
 Thickness (Nominal) 1.5 mm; 60 mils
 Roll Size 65'8" x 39 3/8" (20m x 1m)
 Rolls/Pallet..... 20

APPLICABLE STANDARDS

- ASTM D1970, D5147
- UL Classified for use in class A, B or C roofs, as listed in the latest UL "Roofing Materials and Systems Directory"
- ICC ESR-1697
- Florida Building Code
- Miami Dade Code Compliance



PRODUCT WARRANTY

Polyglass U.S.A., Inc. commercial roofing membranes can be backed with a manufacturer's warranty for up to 20 years when used as part of an approved, multi-ply roofing system. Please see your Polyglass U.S.A., Inc. Sales or Technical Representative for specifications and details



www.polyglass.us

POLYSTICK® MTS

SELF-ADHERED HIGH TEMPERATURE ROOF UNDERLAYMENT

APPLICATION INSTRUCTIONS

- Polystick MTS may be applied directly to the roof deck where allowable by Code.
- Do not apply directly on to existing shingles or other roof coverings.
- Apply only when the substrate is dry and project related temperatures (air, roof deck, membrane) are 40° F and rising.
- Cut the Polystick MTS to a suitable, workable length prior to placement.
- Lay the material flat in place, starting at the lowest point. Overlap seams 3" minimum side laps and 6" minimum.
- Peel half of the release film from the roll and apply firm, even pressure from the center to the outer edge. Remove the backing from the remaining half of the roll and apply pressure.
- Be sure to follow all local building code recommendations and requirements with regards to the width of ice dam materials.
- If full roof coverage application is desired, proper venting of the structure is recommended. Consult a design professional for proper venting requirements. Applications involving non-ventilated attics or sheathing with radiant barriers, an anchor sheet is recommended to allow venting and prevent the creation of a double vapor barrier condition.
- In steep slope applications of 2:12 slope or higher where back nailing may be recommended, be sure that all nails are covered by the overlapping next sheet.
- Polystick MTS must be covered within 180 days of installation or unless otherwise limited by the Authority Having Jurisdiction.

MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.us

General Line: (888) 410-1375
(954) 233-1330
Customer Service: (800) 222-9782
Technical Service: (866) 802-8017

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 1 year.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control. For most current product data and warranty information, visit www.polyglass.us