

DECK
FASTENER

APPLY PB 72
WITH FABRIC OVER
EVERY SCREW.

VERTICAL SEAM 6"
REINFORCING STRIP
OVER BASE COAT
AND DECK JOINT.

SURFACE
COAT

BASE COAT

METAL ROOF DECK.

PLAN

HORIZONTAL SEAM 12" MIN.
REINFORCING STRIP OVER
BASE COAT AND DECK JOINT.

NOTE:

PROVIDE REINFORCING STRIP OVER ALL DECK JOINTS.

- SURFACE COAT POLYBRITE 70 OR PG 700 ELASTOMERIC ROOF COATINGS. APPLY A MINIMUM OF 2 COATS.
- BASE COAT POLYBRITE 70, POLYBRITE 76, OR PG 700 ELASTOMERIC ROOF COATINGS. APPLY A MINIMUM OF 2 COATS.
- FLASHING COMPOUND POLYBRITE 72 FLASHING COMPOUND AS REQUIRED. APPLY AT 1/8" THICK AT EXPOSED FASTENERS.
- POLYESTER POLYBRITE REINFORCING POLYESTER. *REQUIRED FOR POLYGLASS COATING SYSTEM WARRANTY. OPTIONAL; OTHER POLYGLASS EXTENDED MANUFACTURER'S WARRANTIES.
- SURFACE PREPARATION IF OXIDATION IS PRESENT, GRINDING AFFECTED AREAS WITH WIRE BRUSH IS NECESSARY. THEN PRIME ENTIRE ROOF WITH POLYBRITE 74 RUST INHIBITOR PRIMER APPLIED AT THE RATE OF 18-24 WET MILS (150-180 SQUARE FEET PER GALLON).

TYPICAL METAL ROOF JOINT DETAIL

NUMBER:

PG-MRS-448

DATE:

MARCH 2014



www.polyglass.com