

POLYPUF H-1 PART A

ISOCYANATE FOR POLYPUF FOAM SYSTEM

PRODUCT DESCRIPTION

PolyPUF H-1 Part A is a polymeric MDI and it is suitable for the production of rigid insulation foams by molding, spraying, and frothing.

USES

- Spray applied roofing system.
- Offers sustainability and high-performance.
- Applied directly to most existing substrates for new and retrofit installations.
- Provides the highest insulation values.
- Acts as an air barrier, insulation and roofing system in a single application.

FEATURES AND BENEFITS

- Seamless and self-flashing, no seams or laps that are potential future leaks.
- Waterproof throughout the entire thickness of application.
- Provides the most waterproofing protection of any roofing system available.
- Easily maintained for one of the lowest life cycle cost roofing installation.
- Energy efficient, high R-value system.
- May be surfaced in a variety of colors, including highly reflective materials.

TYPICAL PROPERTIES

PROPERTY	VALUE
Appearance	dark brown liquid
NCO content, wt. %	31.5
Viscosity @ 25°C, cps	200
Hydrolyzable chlorine, wt. %	0.035
Flash point, °C (COC)	200
Density @ 25°C, g/cm ³	1.23
Weight per Gallon	10.25
Initial boiling point, 5mm Hg, °C	190
Vapor pressure @ 25°C, mm Hg	0.0002

STORAGE

PolyPUF H-1 Part A is supplied in drums. Once a container has been opened, care should be taken to exclude moisture. The most favorable temperature for storage is 15–35°C. If stored at higher temperatures, or if moisture is not excluded, an undesirable increase in viscosity will occur. Below 15°C, the product becomes difficult to pump and pour. Below 0°C, crystallization may occur. The shelf life of PolyPUF H-1 Part A is nine months if the temperature is maintained at 15–35°C and moisture is excluded.

WARNING

These products can be used to prepare a variety of polyurethane products. Polyurethanes are organic materials and must be considered combustible.

IN CASE OF AN EMERGENCY

Call CHEMTREC (800) 424-9300, day or night for assistance or information concerning spilled material, fire, exposure, and other chemical accidents. Outside the U.S., call (703) 527-3887

APPLICABLE STANDARDS

- UL Classified – File #R14571
- FM Approved



PACKAGING

- 500# Drum

POLYPUF H-1 PART A

ISOCYANATE FOR POLYPUF FOAM SYSTEM

IMPORTANT

While the descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, it is provided for your guidance only. Because many factors may affect processing or application/use, we recommend that you make tests to determine the suitability of a product for your particular purpose prior to use. NO WARRANTIES OF ANY KIND, EITHER EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, ARE MADE REGARDING PRODUCTS DESCRIBED OR DESIGNS, DATA OR INFORMATION SET FORTH, OR THAT THE PRODUCTS, DESIGNS, DATA OR INFORMATION MAY BE USED WITHOUT INFRINGING THE INTELLECTUAL PROPERTY RIGHTS OF OTHERS. IN NO CASE SHALL THE DESCRIPTIONS, INFORMATION, DATA OR DESIGNS PROVIDED BE CONSIDERED A PART OF OUR TERMS AND CONDITIONS OF SALE. Further, you expressly understand and agree that the descriptions, designs, data, and information furnished by Polyglass U.S.A. Inc. hereunder are provided gratis Polyglass U.S.A. Inc. assumes no obligation or liability for the description, designs, data and information given or results obtained, all such being given and accepted at your risk.

MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Phoenix, AZ
- Waco, TX
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.us

General Line: (888) 410-1375
(954) 233-1330

Customer Service: (800) 222-9782

Technical Service: (866) 794-9659

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects that result in the material not complying with product specifications for a period of 12 months.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances. The product user, and not Polyglass, is responsible for determining the suitability and compatibility of our products for the user's intended use.

For the most current product data and warranty information, visit www.polyglass.us



www.polyglass.us