ELASTOFLEX SA BASE

SELF-ADHERED SBS (ELASTOMERIC) BASE SHEET

PRODUCT DESCRIPTION

Elastoflex SA Base membrane is a self-adhered, elastomeric base ply low-slope roofing product. Elastoflex SA Base is manufactured using patented ADESO® dual-compound self-adhered technology, whereby a "true" Styrene-Butadiene-Styrene (SBS) modified asphalt compound is applied on the top layer and a proprietary self-adhesive SBS compound is applied to the bottom. Elastoflex SA Base membrane is built with a durable non-woven polyester mat to enhance tear strength and puncture resistance, providing a robust membrane that resists natural forces and other factors on the rooftop.

Elastoflex SA Base membrane is finished with a film with pre-printed laylines on the top surface and a split release film on the bottom surface.

Elastoflex SA Base can be used as part of a Polyglass warranted multi-ply system with Elastoflex SA P or other approved Polyglass cap sheet to provide cleaner application, improved application speed and removes the need for torches, hot asphalt or bonding adhesives on the job site.

TYPICAL APPLICATIONS

- Standard new construction and re-roofing applications.
- For use as a base or interply sheet with approved Polyglass roofing systems.
- Job sites with limited access for special installation equipment or where using a propane torch, hot asphalt or adhesives is undesirable.

FEATURES AND BENEFITS

- Application directly to approved insulation, cover boards and wood decks without a primer**
- Durable non-woven polyester mat enhances tear and puncture resistance
- Premium SBS compound provides enhanced long-term weathering performance
- Adhere approved SA cap/interply sheet directly to Elastoflex SA Base without a primer*
- Quick dry-in of building and up to 90 day exposure time*

TECHNICAL DESCRIPTION**

Physical Properties	ASTM Method	ASTM Value	Typical Performance
Peak Load at 0°F (-18°C)	D5147	70 lbf/in (12.3 kN/m)	174 lbf/in (30.5 kN/m) - MD 123 lbf/in (21.5 kN/m) - XMD
Elongation at Peak Load at 0°F (-18°C	D5147	20%	58% - MD 64% - XMD
Peak Load at 73°F (23°C)	D5147	50 lbf/in (8.8 kN/m)	107 lbf/in (18.7 kN/m) - MD 82 lbf/in (14.4 kN/m) - XMD
Elongation at Peak Load at 73°F (23°C)	D5147	35%	65% - MD 77% - XMD
Ultimate Elongation at 73°F (23°C)	D5147	38%	74% - MD 84% - XMD
Tear Strength at 73°F (23°C)	D5147	55 lbf (246 N)	155 lbf (689 N) - MD 121 lbf (538 N) - XMD
Low Temperature Flexibility (maximum)	D5147	0°F (-18°C)	< 0°F (-18°C)
Dimensional Stability (maximum)	D5147	1%	0% - MD 0% - XMD
Compound Stability (minimum)	D5147	215°F (102°C)	pass
Moisture Vapor Permeance, max	E96	max 0.1 U.S. Perms (5.7 ng/Pa.S.M²)	pass

 $[\]ensuremath{^{\star\star}}\xspace$ The properties in this table are "as manufactured" unless otherwise noted





***All values are nominal at time of manufacturing

APPLICABLE STANDARDS

- ASTM D6164, Type 1, Grade S
- UL Classified
- FM Approved
- Florida Building Code
- Miami-Dade County Product Control Approved









PRODUCT CODES

• EP25SACHDQ



^{*}See suitable substrates Polyglass Technical Bulletin #2012-02

ELASTOFLEX SA BASE

SELF-ADHERED SBS (ELASTOMERIC) BASE SHEET

APPLICATION INSTRUCTIONS

Elastoflex SA Base is intended to be used as a base/interply sheet in a multi-ply low slope roof system when applied to acceptable insulations and/or coverboards for commercial structures. Elastoflex SA Base may also be applied directly to approved wood deck substrates of non-occupied spaces such as carports, sheds, canopies, etc. For additional substrate requirements and information refer to Polyglass published "Suitable Substrates for Self-Adhered (SA) Membranes."

- Apply Elastoflex SA Base membrane only in dry weather and when air and surface temperatures are 40°F (5°C) and rising.
- Apply over clean, dry, dust and debris-free substrates. Prime required substrates prior to application with PG 100 Fast-Drying Asphalt Primer or alternative ASTM D41 primers as approved by Polyglass.
- When re-roofing, remove all prior roofing materials down to a clean debris free substrate and properly close off all abandoned roof penetrations.
- Concrete or Steel decks shall be designed with proper expansion devices.
- Wood decks shall be properly supported by the structural framina.
- Ensure the installation of Elastoflex SA Base does not prevent the ventilation of existing construction
- Do not apply directly to shingles or other granulated surface roof systems.
- While installing Elastoflex SA Base:
 - 1. Start at the low point of the roof.
 - 2. Unroll the material and allow to relax.
 - 3. Start by removing the first 18-24" of release film.
 - 4. Press the membrane into place with firm and even pressure.
 Roll the edges with a silicone hand roller to ensure complete adhesion.
 - 5. Gradually remove the remaining release film applying pressure from the center to the edges as you go.
 - 6. Position successive rolls providing a minimum 6" end lap and 3" side lap. Laps can be sealed for additional water tightness with a hot air welder.
 - 7. Roll with an 75# split-face linoleum roller. Take care on sloped roofs by securing the roller and applicator with the appropriate safety equipment. Intermittent rolling is recommended to ensure complete contact to underlying surface.

Details and flashing may be installed using Elastoflex SA Base with a hot air welder or with PG 500 Roof Cement or PolyPlus 50 Premium Modified Wet/Dry Cement. Check project details for proper installation requirements.

MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Waco, TX
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc. 1111 West Newport Center Drive Deerfield Beach, FL 33442 www.polyglass.us

General Line: (888) 410-1375 (954) 233-1330 Customer Service: (800) 222-9782 Technical Service: (866) 794-9659

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 2 years.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control. For most current product data and warranty information, visit www.polyglass.us.

