

POLYFLEX® 5.0

APP (PLASTOMERIC) MEMBRANE

PRODUCT DESCRIPTION

Polyflex 5.0 membranes are premium, polyester reinforced APP (plastomeric) modified bitumen roofing products specially designed for heat-welded applications. Constructed with a premium APP (plastomeric) compound, and incorporating superior non-woven polyester reinforcing, Polyflex 5.0 provides an exceptionally robust and durable roofing product which is easy to install and will provide long-term weathering performance that resists natural forces and other factors on the rooftop.

The top is constructed with a smooth sand surface while the bottom has a factory applied burn-off film.

Successive system layers can be heat welded with an additional ply of Polyflex 5.0 or Polyflex G cap sheets.

TYPICAL APPLICATIONS

- Heat-welded base, interply or cap sheet.
- Applied directly over an acceptable substrate or as part of a multi-ply system.
- New roofing, re-roofing, re-cover and for flashing details.

FEATURES AND BENEFITS

- Robust membrane with exceptional weathering characteristics.
- Puncture and tear resistance.
- Low-temp flexibility, superior tensile strength and elongation properties.

TECHNICAL DESCRIPTION*

Physical Properties	ASTM Method	ASTM Value	Typical Performance
Peak Load at 73°F [23°C]	D5147	50 lbf/in. [8.8 kN/m]	106 lbf/in [18.6 kN/m] MD 72 lbf/in [12.6 kN/m] XMD
Elongation at Peak Load at 73°F [23°C]	D5147	23%	48% MD 61% XMD
Peak Load at 0°F [-18°C]	D5147	60 lbf/in. [10.5 kN/m]	154 lbf/in. [27.0 kN/m] MD 112 lbf/in. [19.6 kN/m] XMD
Elongation at Peak Load at 0°F [-18°C]	D5147	10%	42% MD 43% XMD
Ultimate Elongation at 73°F [23°C]	D5147	30%	56% MD 69% XMD
Tear Strength at 73°F [23°C]	D5147	70 lbf [311 N]	140 lbf [623 N] MD 98 lbf [436 N] XMD
Low Temperature Flexibility [maximum]	D5147	32°F [0°C]	Pass
Dimensional Stability [maximum]	D5147	1%	0.01%
Compound Stability [maximum]	D5147	230°F [110°C]	Pass
Water Absorption [maximum]	D5147	3.20%	0.60%
Moisture Content [maximum]	D5147	1%	0.3%
Low Temperature Unrolling [maximum]	D5147	41°F [5°C]	Pass

*The properties in this table are "as manufactured" unless otherwise noted



PRODUCT DATA**

Coverage (Approx) 100 sq ft (9.3 m²)
 Weight (Approx) 123 lbs (56 kg)
 Thickness (Nominal) 197 mils (5.0 mm)
 Roll Size 32'10" x 39 3/8" (10 m x 1 m)
 Rolls/Pallet 20

**All values are nominal at time of manufacturing

APPLICABLE STANDARDS

- ASTM D6222, Type I, Grade S
- UL Classified
- FM Approved
- ICC ESR-2018
- Miami-Dade County Approved
- Texas Department of Insurance



PRODUCT CODES

- PF50SPZ



www.polyglass.us

POLYFLEX® 5.0

APP (PLASTOMERIC) MEMBRANE

APPLICATION INSTRUCTIONS

Polyflex 5.0 is intended to be used as a base, interply or cap sheet in new or re-roof applications. Polyflex 5.0 may be applied directly to non-combustible substrates. Polyflex 5.0 requires the installation of a compatible granulated cap sheet or approved roof coating to complete the roofing system.

- Apply over clean, dry, dust and debris-free substrates. Prime concrete decks and required substrates prior to application with PG 100 Fast-Drying Asphalt Primer. Consult Polyglass Technical Service if alternate primer is allowed.
- When re-roofing, remove all prior roofing materials down to a clean debris-free substrate and properly close-off all abandoned roof penetrations.
- Concrete or steel decks shall be designed with proper expansion devices.
- Wood decks shall have all joints blocked and properly supported.
- Ensure the fire rating of the assembly over any combustible substrate.
- Ensure the installation of Polyflex 5.0 does not prevent the ventilation of existing construction.
- Do not apply over shingles or any granulated surface.
- While installing Polyflex 5.0:
 1. Start at the low point of the roof.
 2. Unroll the material and allow to relax.
 3. Install with traditional torch roofing techniques ensuring proper heating of the roofing material as not to expose the reinforcement.
 4. Do not heat the substrate.
 5. Position successive rolls providing a minimum 6" end lap and 3" side lap. Asphalt bleed out shall be 1/4" to 3/8" on all seams.
 6. It is suggested but not mandatory that laps shall be rolled with a 6"-wide roller immediately after heat welding.
- Details and flashing may be installed using Polyflex 5.0 with torch applied techniques. Do not use cold adhesives or hot asphalt. Check project details for proper installation requirements.
- For detailed drawings and recommended installation procedures of typical roof segments, such as drip edge and joint conditions, please refer to our website at, www.polyglass.us.

MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Waco, TX
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.us

General Line: (888) 410-1375
(954) 233-1330

Customer Service: (800) 222-9782
Technical Service: (866) 802-8017

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 5 years.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control. For most current product data and warranty information, visit www.polyglass.us



www.polyglass.us