

POLYBRITE® 23

ELASTOMERIC BASE COATING

PRODUCT DESCRIPTION

PolyBrite 23 is a roller-grade, water-based, grey styrene acrylic base coating which cures to form a seamless membrane. This product offers the unique ability to extend the life of a roofing system, and lower overall life cycle costs.

USES

- Protect and waterproofs a variety of roof surfaces.
- Suitable for use on a variety of roof surfaces such as BUR and granulated modified bitumen membranes. Also approved over most metal roof systems and PVC single ply, concrete, exterior-grade plywood, and most rigid cover boards. Usage to certain substrates may be limited or require additional preparation.

FEATURES AND BENEFITS

- Easy application.
- Resistant to dirt pick-up.
- Fungal and algal resistant.
- Low VOC, non-flammable and presents minimal hazard to the applicator.


TYPICAL PHYSICAL PROPERTIES

TEST PROPERTY	TEST VALUE	TEST PROCEDURE
Accelerated Weathering @1000 hr. (Pass/fail)	Pass	ASTM D4798
Permeance (perms)	10 – 15	ASTM D1653
Fungi Resistance (Pass/Fail)	Pass	ASTM G21
Elongation (%)	200 ± 20	ASTM D2370
Tensile Strength (psi)	350 ± 25	ASTM D2370
Viscosity (cP)	48,000 – 60,000	ASTM D2196
Weight Per Gal	12 ± 0.5	ASTM D2939
Solids Weight (%)	66 ± 2	ASTM D1644
Solids Volume (%)	55 ± 2	ASTM D2697
VOC (g/l)	< 50	Calculated
pH (rating)	9	Standard Method
Flash Point (°F)	> 200	PMCC

APPLICATION INSTRUCTIONS

Surface Preparation:

- All surfaces to receive coating must be clean, dry, and free from any foreign matter such as dirt, oils, grease, or other debris that could inhibit the adhesion capabilities of the newly installed product.
- Existing roof system to be visually inspected for conditions that may adversely affect adhesion of newly installed products. Repair any visible deficiencies such as splitting, blistering, and buckling.
- Visually inspect all metal and non-metal flashings, edges, drains, valleys, and through-roof penetrations and repair as needed by project conditions.
- Do not apply to wet or visibly damp surfaces, or surfaces previously covered with coal tar-based products or Kynar® finishes.
- Concrete surfaces cured with wax/resin-based compounds can inhibit adhesion.



PACKAGING

- 5 Gallon (18.9 Liters) Pail
- 55 Gallon (208 Liters) Drum
- 250 Gallon (946 Liters) Tote

COLORS

Kool Grey



POLYGLASS®



www.polyglass.us

POLYBRITE® 23

ELASTOMERIC BASE COATING

Application:

- Stir well prior to application.
- PolyBrite 23 may be applied by roller.
- Apply PolyBrite 23 at 24 wet mils (1.5 gallon per 100 square feet) per coat.
- Apply only when ambient temperatures are 50°F and rising. Cold weather could result in uneven application and improper curing of product. Do not apply if there is a threat of inclement weather within 24 hours of application.
- Do not thin product. Do not heat outside of container. Do not apply at temperatures greater than 120°F.
- Prior to using this product on new cap sheets (smooth or granulated), it is recommended to wait 30 days for weathering.

Storage and Cleaning:

- Shelf life is 18 months if stored in original unopened containers.
- All containers should be sealed when not in use.
- Keep from freezing.
- Store between 40°F and 100°F.
- Observe normal safeguards for storing and handling of this product prior to and during application.
- Clean equipment and overspray with water.
- Clean hands with waterless hand cleaner.
- Application tools and equipment can be cleaned with lukewarm water and soap, followed by a rinse of isopropanol, acetone, or Simple Green®. Recirculate through lines and gun until residual coating is removed.
- DO NOT USE MINERAL SPIRITS, XYLENE, TOLUENE, OR VMP & NAPHTHA SOLVENTS.

For Professional Use Only - Keep out of the reach of children.

MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Phoenix, AZ
- Waco, TX
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.us

General Line: (888) 410-1375
(954) 233-1330

Customer Service: (800) 222-9782

Technical Service: (866) 794-9659

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects that result in the material not complying with product specifications for a period of 12 months.

Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances. The product user, and not Polyglass, is responsible for determining the suitability and compatibility of our products for the user's intended use.

For the most current product data and warranty information, visit www.polyglass.us