

# POLYGLASS® PRIMER PUc-1050

## TWO-COMPONENT POLYURETHANE PRIMER DESIGNED FOR COLD TEMPERATURE APPLICATIONS WITH THE TECNOCOAT MEMBRANE SYSTEMS

### PRODUCT DESCRIPTION

Polyglass Primer PUc-1050 is a two-component, 100% solids polyurethane resin designed to increase adhesion between substrates and Tecnocoat membrane systems.

### FEATURES AND BENEFITS

- 10 kg, 1:1 kit
- Pot life: 45 minutes
- Dry time 3 hours
- Coverage @ 7 mils 530 ft<sup>2</sup>/kit
- Roller, brush or spray application
- Above 40°F on concrete
- Can be installed at 32°F and rising

### TECHNICAL DESCRIPTION

Properties	Value
Viscosity	700 cps
Density	1.11 g/cm <sup>3</sup>
Mix Ratio	1:1
Solids Content	100%
VOC Content	0
Hardness Shore A	80
Adhesion to Concrete	525 psi
Application Temperature Range	32°F and rising
Pot Life	45 minutes
Dry time	3 hours

### LIMITATIONS

Not for use on metal substrates. For metal substrates see Primer EP-1020 and refer to applicable Technical Data Sheets.

### STORAGE AND SHELF LIFE

12 months shelf life if stored in original containers in a dry environment at a temperature between 40°F–95°F. Keep away from direct sunlight, extreme heat, cold or moisture.

### SURFACE PREPARATION

Concrete substrates must be allowed to cure for 28 days. All laitance, surface / release treatments, or other contaminants must be removed. Concrete must have a ICRI surface profile of 3–5, which is typically best accomplished by mechanical preparation.



### PRODUCT DATA

Application method.... Roller, brush or spray

### PACKAGING

#### Metallic pail kit (10 kg):

Part A 5 kg  
Part B 5 kg

### PRODUCT CODES

- 0192710UPY Part A 5 kg
- 0192910UPY Part B 5 kg



[www.polyglass.us](http://www.polyglass.us)

# POLYGLASS® PRIMER PUc-1050

## TWO-COMPONENT POLYURETHANE PRIMER DESIGNED FOR COLD TEMPERATURE APPLICATIONS WITH THE TECNOCOAT MEMBRANE SYSTEMS

### APPLICATION

#### TEMPERATURE

The substrate and ambient temperature must be between 32°F and 95°F with a concrete moisture content of less than 5%. For applications below 32°F consult Polyglass Technical Services.

Both Parts A & B are sensitive to moisture, ensure the pails are protected from moisture during storage and application.

#### MIXING AND APPLICATION

After opening, both Parts A and B, slowly pour the entire contents of Part B into the Pail of Part A. Mix for approximately 4–5 minutes and ensure a uniform color. Do not overmix or entrap air.

Immediately after mixing, apply to the substrate by roller, brush, or airless sprayer.

Primer PUc-1050 should be applied in thin coats, not to exceed 7 mils in one application.

Primer PUc-1050 can be applied in conjunction with silica sand to remediate small surface defects in concrete substrates.

Ensure Tecnocoat waterproofing membranes are applied within 24 hours of the Primer PUc-1050 application.

### CLEANING

- Tools can be cleaned with Xylene or MEK

### HEALTH AND SAFETY:

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking, or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Dispose waste in accordance with federal, state, and local regulations.

### CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.  
1111 West Newport Center Drive  
Deerfield Beach, FL 33442  
[www.polyglass.us](http://www.polyglass.us)

General Line: (888) 410-1375  
(954) 233-1330

Customer Service: (800) 222-9782  
Technical Service: (866) 794-9659

**Questions?** [technical@polyglass.com](mailto:technical@polyglass.com)

#### Product Disclaimer:

For professional use only.

Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 1 year. Refer to safety data sheet (SDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances. Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control. For most current product data, detail drawings and warranty information, visit [www.polyglass.us](http://www.polyglass.us)