



# SILICONE COATINGS MATRIX

Polyglass Product	Single Ply Membranes	Metal Roofs	Smooth Mod Bit or Smooth BUR	Granulated Mod-Bit	Concrete	Roof Foam
<b>PolyBrite® 78</b> Rinseable EPDM Primer	500 sq. ft./gal. (Sprayer Only)	N/A	N/A	N/A	N/A	N/A
<b>PolyBrite® 79</b> Solvent-based TPO Primer	300-400 sq. ft./gal. (TPO Only)	N/A	N/A	N/A	N/A	N/A
<b>PolyBrite® 84</b> Rust Inhibitive Primer	N/A	200-300 sq. ft./gal.	N/A	N/A	N/A	N/A
<b>PolyBrite® 98</b> Acrylic Primer/Bleed Blocker	200-300 sq. ft./gal. (PVC Only)	N/A	150-200 sq. ft./gal.	100-150 sq. ft./gal.	100-200 sq. ft./gal.	N/A
<b>PolyBrite® 90 Series</b> High-Solids Premium Silicone Coating	10 Yr = 1.5 Gal/Sq 15 Yr = 2.0 Gal/Sq 20 Yr = 2.5 Gal/Sq	10 Yr = 1.5 Gal/Sq 15 Yr = 2.0 Gal/Sq 20 Yr = 2.5 Gal/Sq	10 Yr = 1.5 Gal/Sq 15 Yr = 2.0 Gal/Sq 20 Yr = 2.5 Gal/Sq	10 Yr = 1.5 Gal/Sq 15 Yr = 2.0 Gal/Sq 20 Yr = 2.5 Gal/Sq	10 Yr = 1.5 Gal/Sq 15 Yr = 2.0 Gal/Sq 20 Yr = 2.5 Gal/Sq	10 Yr = 1.5 Gal/Sq 15 Yr = 2.0 Gal/Sq 20 Yr = 2.5 Gal/Sq
	10 Yr = 24 WFT/23 DFT 15 Yr = 32 WFT/30 DFT 20 Yr = 40 WFT/38 DFT	10 Yr = 24 WFT/23 DFT 15 Yr = 32 WFT/30 DFT 20 Yr = 40 WFT/38 DFT	10 Yr = 24 WFT/23 DFT 15 Yr = 32 WFT/30 DFT 20 Yr = 40 WFT/38 DFT	10 Yr = 24 WFT/23 DFT 15 Yr = 32 WFT/30 DFT 20 Yr = 40 WFT/38 DFT	10 Yr = 24 WFT/23 DFT 15 Yr = 32 WFT/30 DFT 20 Yr = 40 WFT/38 DFT	10 Yr = 24 WFT/23 DFT 15 Yr = 32 WFT/30 DFT 20 Yr = 40 WFT/38 DFT
	10 Yr = 2.0 Gal/Sq 15 Yr = 2.5 Gal/Sq 20 Yr = 3.0 Gal/Sq	10 Yr = 2.0 Gal/Sq 15 Yr = 2.5 Gal/Sq 20 Yr = 3.0 Gal/Sq	10 Yr = 2.0 Gal/Sq 15 Yr = 2.5 Gal/Sq 20 Yr = 3.0 Gal/Sq	10 Yr = 2.0 Gal/Sq 15 Yr = 2.5 Gal/Sq 20 Yr = 3.0 Gal/Sq	10 Yr = 2.0 Gal/Sq 15 Yr = 2.5 Gal/Sq 20 Yr = 3.0 Gal/Sq	10 Yr = 2.0 Gal/Sq 15 Yr = 2.5 Gal/Sq 20 Yr = 3.0 Gal/Sq
<b>PolyBrite® 95 Series</b> Solvent-Based Silicone Coating	10 Yr = 32 WFT/22 DFT 15 Yr = 40 WFT/27 DFT 20 Yr = 48 WFT/33 DFT	10 Yr = 32 WFT/22 DFT 15 Yr = 40 WFT/27 DFT 20 Yr = 48 WFT/33 DFT	10 Yr = 32 WFT/22 DFT 15 Yr = 40 WFT/27 DFT 20 Yr = 48 WFT/33 DFT	10 Yr = 32 WFT/22 DFT 15 Yr = 40 WFT/27 DFT 20 Yr = 48 WFT/33 DFT	10 Yr = 32 WFT/22 DFT 15 Yr = 40 WFT/27 DFT 20 Yr = 48 WFT/33 DFT	10 Yr = 32 WFT/22 DFT 15 Yr = 40 WFT/27 DFT 20 Yr = 48 WFT/33 DFT
<b>PolyFlash® 1C</b> <sup>1,3</sup> 1-Part Flashing Compound	4.0 Gal/Sq. 64 WFT/ 52 DFT	4.0 Gal/Sq. 64 WFT/ 52 DFT	4.0 Gal/Sq. 64 WFT/ 52 DFT	4.0 Gal/Sq. 64 WFT/ 52 DFT	4.0 Gal/Sq. 64 WFT/ 52 DFT	4.0 Gal/Sq. 64 WFT/ 52 DFT
1 Gallon applied at 32 Wet Mills (26 Dry Mills) 6" wide will theoretically cover 100 lineal feet						
<b>PolyBrite® 93</b> <sup>1,2</sup> Silicone Flashing Compound	2.5 gal/sq. 40 WFT/39 DFT	250 - 300 fasteners per gallon, approx.	2.5 gal/sq. 40 WFT/39 DFT	2.5 gal/sq. 40 WFT/39 DFT	2.5 gal/sq. 40 WFT/39 DFT	2.5 gal/sq. 40 WFT/39 DFT
1 Gallon applied at 32 Wet Mills (26 Dry Mills) 6" wide will theoretically cover 100 lineal feet						

- 1 - The amount listed represents the total volume of product required when applied using the three-course method, including both layers—  
under and over the fabric.  
2 - Approx. 250-350 fasteners or 75-100 lf. at 4" wide per 1 Gallon  
3 - This product is to be applied only over approved systems and exclusively prior to the installation of silicone roof coatings. It is not approved for  
use over silicone-coated surfaces.

## Warranty Fees:

NDL - 10 Year \$.05 per square foot or \$500 Minimum.  
NDL - 15 Year \$.07 per square foot or \$700 Minimum.  
NDL - 20 Year \$.09 per square foot or \$900 Minimum.